BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images, please do not report the images to the Image Problem Mailbox.

Attorney's Docket: 1999DE132
Serial No.: 09/722,760
Group: 1756

AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A method of imparting, controlling or improving the charge of an electrophotographic toner or developer, or an electret material, comprising the step of adding a structured silicate salt ~~in which the cation is~~ contains a low molecular weight organic cation and the anion is an island, cyclic, group, chain, ribbon, laminar or matrix silicate or a combination thereof to a binder of an electrophotographic toner or developer or of an electret material.

2) (Cancelled)

3) (Cancelled)

4) (Original) The method as claimed in claim 1, wherein the low molecular weight organic cation is a substituted ammonium, phosphonium, thionium or triphenylcarbonium ion or a cationic metal complex.

5) (Currently Amended) The method as claimed in claim 4, wherein the ammonium ion has one of the formulae (a) - (j)



(a)



(b)



(c)



(d)



(e)



(f)



(g)



(h)

Attorney's Docket: 1999DE132
Serial No.: 09/722,760
Group: 1756



(I)



(J)

in which

R^1 to R^{18} are identical or different and represent hydrogen, CN, $(CH_2)_{1-18}CN$, halogen, branched or unbranched C_1-C_{32}-alkyl, mono- or polyunsaturated C_2-C_{32}-alkenyl, C_1-C_{22}-alkoxy, C_1-C_{22}-hydroxyalkyl, C_1-C_{22}-halogenoalkyl, C_2-C_{22}-halogenoalkenyl, C_1-C_{22}-aminoalkyl, $(C_1$-$C_{12})$-trialkyl-ammonium-$(C_1$-$C_{22})$-alkyl; $(C_1$-$C_{22})$-alkylene-(C=O)O-$(C_1$-$C_{32})$alkyl, $(C_1$-$C_{22})$-alkylene-(C=O)O-aryl, $(C_1$-$C_{22})$-alkylene-(C=O)NH-$(C_1$-$C_{32})$alkyl, $(C_1$-$C_{22})$-alkylene-(C=O)NH-aryl, $(C_1$-$C_{22})$-alkylene-O(CO)-$(C_1$-$C_{32})$alkyl, $(C_1$-$C_{22})$-alkylene-O(CO)aryl, $(C_1$-$C_{22})$-alkylene-NH(C=O)-$(C_1$-$C_{32})$alkyl, $(C_1$-$C_{22})$-alkylene-NHCO-aryl,

wherein

 or  ,

are optionally inserted into the acid ester or acid amide bonds;

$[(C_1$-$C_{12})$-alkylene-O-$]_{1-100}$-H; aryl, $(C_1$-$C_{18})$-alkylenearyl; $-(O\text{-}SiR'_2)_{1-32}$-O-SiR'$_3$, in which R' has the meaning C_1-C_{12}-alkyl, phenyl, benzyl or C_1-C_{12}-alkoxy; heterocyclyl, C_1-C_{18}-alkylene-heterocyclyl, wherein the aryl and heterocyclyl radicals are optionally mono- or polysubstituted on carbon atoms or heteroatoms by C_1-C_{12}-alkyl, C_1-C_4-alkenyl, C_1-C_4-alkoxy, hydroxy-$(C_1$-$C_4)$alkyl, amino-$(C_1$-$C_4)$alkyl, C_1-C_4-alkylimino, carboxyl, hydroxyl, amino, nitro, cyano, halogen, C_1-C_{12}-acyl, C_1-C_4-halogenoalkyl, C_1-C_4-alkylcarbonyl, C_1-C_4-alkylcarbonyloxy, C_1-C_4-alkoxycarbonyl, C_1-C_4-

alkylaminocarbonyl, C_1-C_4-alkylcarbonylimino, C_6-C_{10}-arylcarbonyl, aminocarbonyl, aminosulfonyl, C_1-C_4-alkylaminosulfonyl, phenyl, naphthyl, or heteroaryl[-];

R^{19} represents C_4-C_{11}-alkylene, $-(C_2H_4-O-)_{1-17}-(CH_2)_{1-2}-$, $-(C_2H_4-NR-)_{1-17}-(CH_2)_{1-2}-$, in which R is hydrogen or C_1-C_{12}-alkyl;
X has the meaning of Y or $-CO-CH_2-CO-$,



,



,



,

1/2



,

1/2



or

1/2



;

Y has the meaning $-C(=O)-$, $-C(=S)-$, $-C(=NH)-$, $-(CH_2)_{1-18}-$,

BEST AVAILABLE COPY



or o-, p-, m-(C_6-C_{14})-arylene or (C_4-C_{14})-heteroarylene with 1, 2, 3 or 4 heteroatoms selected from the group consisting of N, O, S and a combination thereof;

R^{60} represents C_1-C_{32}-acyl, C_1-C_{22}-alkyl, C_2-C_{22}-alkenyl, C_1-C_{18}-alkylene-C_6-C_{10}-aryl, C_1-C_{22}-alkylene-heterocyclyl, C_6-C_{10}-aryl or (C_4-C_{14})-heteroaryl with 1, 2, 3 or 4 heteroatoms selected from the group consisting of N, O, S, and a combination thereof;

R^{61} and R^{64} represent -$(CH_2)_{1-18}$-, C_1-C_{12}-alkylene-C_6-C_{10}-arylene, C_6-C_{10}-arylene, C_0-C_{12}-alkylene-heterocyclyl;

Z represents -NH- or -O- ;

A_1^- and A_3^- represent $-COO^-$, $-SO_3^-$, $-OSO_3^-$, $-SO_2^-$, $-COS^-$ or $-CS_2^-$;

A_2 represents $-SO_2Na$, $-SO_3Na$, $-SO_2H$, $-SO_3H$ or hydrogen;

R^{69} and R^{70} independently of one another represent hydrogen, C_1-C_{32}-alkyl, in which the alkyl chain optionally contain one or more of the groups -NH-CO-, -CO-NH-, -CO-O- or -O-CO-; C_1-C_{18}-alkylene-aryl, C_0-C_{18}-alkylene-heterocyclyl, C_1-C_{18}-hydroxyalkyl, C_1-C_{18}-halogenoalkyl, aryl, $-(CH_2)_3-SO_3^-$,

$-CH_2-\underset{\displaystyle SO_2^-}{\underset{|}{CH}}-CH_2-SO_3^-$, $-CH_2-\underset{\displaystyle SO_3^-}{\underset{|}{CH}}-CH_2-SO_3^-$;

R^{71} and R^{72} represent $-(CH_2)_{1-12}-$; and
R^{73} and R^{74} represent hydrogen or C_1-C_{22}-alkyl.

6) (Original) The method as claimed in claim 5, wherein R^1 to R^{18} denote hydrogen CN, CH_2-CN, CF_3, C_1-C_{22}-alkyl, C_2-C_{18}-alkenyl, C_1-C_{18}-alkoxy, C_1-C_{18}-hydroxy-alkyl, C_1-C_{18}-halogenoalkyl, C_2-C_{18}-halogenoalkenyl, C_1-C_{18}-aminoalkyl, (C_1-C_6)-trialkylammonium-(C_1-C_{18})-alkyl, (C_1-C_{18})-alkylene-O(C=O)-(C_1-C_{22})alkyl, (C_1-C_{18})-alkylene-O(C=O)-phenyl, (C_1-C_{18})-alkylene-NHCO-(C_1-C_{22})alkyl, (C_1-C_{18})-alkylene-NHCO-phenyl, (C_1-C_{18})-alkylene-(C=O)O-(C_1-C_{22})alkyl, (C_1-C_{18})-alkylene-(C=O)O-phenyl, (C_1-C_{18})alkylene-(C=O)NH-(C_1-C_{22})alkyl, (C_1-C_{18})-alkylene-CONH-phenyl, benzyl, phenyl, naphthyl, C_1-C_{12}-alkylene-heterocyclyl;
R^{19} denotes C_4-C_5-alkylene, $-(C_2H_4-O)_{1-9}-(CH_2)_{1-2}-$ or $-(C_2H_4-NH)_{1-9}-(CH_2)_{1-2}-$;
R^{60} denotes C_1-C_{18}-acyl, C_1-C_{18}-alkyl, C_2-C_{18}-alkenyl, C_1-C_{12}-alkylene-phenyl, C_1-C_{18}-alkylene-pyridyl, phenyl or pyridyl;
R^{61} and R^{64} denote $-(CH_2)_{1-12}-$, C_1-C_8-alkylene-phenylene, phenylene or C_1-C_8-alkylenepyridylene or piperidylene;
R^{71} and R^{72} denote $-(CH_2)_{1-8}$ and
R^{73} and R^{74} denote hydrogen or (C_1-C_{18})-alkyl.

7) (Previously Presented) The method as claimed in claim 4, wherein the ammonium ion is an aliphatic or aromatic 5- to 12-membered heterocyclic radical with 1 to 4 atoms selected from the group consisting of N, O and S, or a combination thereof, belonging to the rings.

8) (Original) The method as claimed in claim 7, wherein the heterocyclic radical is pyridinium, pyridazinium, pyrimidinium, pyrazinium, purinium, tetraazaporphyrinium, piperidinium, morpholinium, tetrazonium, triaza-cyclononanium or tetraaza-cyclododecanium.

9) (Original) The method as claimed in claim 4, wherein the cationic metal complex is a metal carboxylate, metal salicylate, metal sulfonate, 1:1 metal-azo complex or a metal dithiocarbamate.

10) (Previously Presented) The method as claimed in claim 9, wherein the metal is selected from the group consisting of Al, Mg, Ca, Sr, Ba, TIO, VO, Cr, V, Ti, Zr, Sc, Mn, Fe, Co, Ni, Cu, Zn and ZrO.

11) (Original) The method as claimed in claim 1, wherein the organic cation is a fluorinated ammonium ion of the formula (x)



(x)

in which
R^{28} denotes perfluorinated alkyl having 5 to 11 carbon atoms and
R^{29}, R^{30} and R^{31} are identical or different and denote alkyl having 1 to 5 carbon atoms.

12) (Original) Salt-like structured silicate, in which the silicate is hectorite, beidellite, illite, muscovite, xantophyllite, margarite, sepiolite, saponite, mica, feldspar, nontronite, montmorillonite, smectite, bentonite, faujasite, zeolite A, X or Y, permutite, sasil or a combination thereof; and the cation is an ion of the formula (x) as claimed in claim 9.

13) (Original) A process for the preparation of a salt-like structured silicate as claimed in claim 12, which comprises combining the silicate and a salt of the cation of formula (x) in an aqueous medium.

14) (Currently Amended) An electrophotographic toner comprising 30 to 99.99% by weight of a binder, and 0.01 to 50% by weight, of at least one salt of ionic structured silicates ~~in~~ which ~~the cation is~~ contains a low molecular weight organic cation and the anion is an island, cyclic, group, chain, ribbon, laminar or matrix silicate or a combination thereof, based on the total weight of the electrophotographic toner.

15) (Previously Presented) An electrophotographic toner as claimed in claim 14, comprising 40 to 99.5% by weight of a binder, and 0.05 to 20% by weight of at least one salt of ionic structured silicates in which the cation is a low molecular weight organic cation and the anion is an island, cyclic, group, chain, ribbon, laminar or matrix silicate or a combination thereof, based on the total weight of the electrophotographic toner.

16. (Previously Presented) The method of claim 4, wherein the ammonium ion is an aliphatic or aromatic 5- to 12-membered heterocyclic radical with 1 to 4 atoms selected from the group consisting of N, O and S, or a combination thereof, belonging to the rings, wherein 2 to 8 rings are fused.

17. (Previously Presented) The method as claimed in claim 9, wherein the metal is selected from the group consisting of Al, Mg, Ca, Sr, Ba, TiO, VO, Cr, V, Ti, Zr, Sc, Mn, Fe, Co, Ni, Cu, Zn and ZrO, and the metal complex contains one or more further ligands.

18. (Currently Amended) A method of imparting, controlling or improving the charge of an electrophotographic toner or developer, of a powder coating, or of an electret material, comprising the steps of adding a salt structured silicate ~~in~~ which ~~the cation is or~~contains a low molecular weight organic cation and the anion is an island, cyclic, group, chain, ribbon, laminar or matrix silicate or a combination thereof to a binder of an electrophotographic toner or developer or of a powder coating, or to an electret material.

19. (Previously Presented) An electrophotographic toner or developer comprising distearyldimethyl ammonium bentonite.

20. (Previously Presented) The electrophotographic toner as claimed in claim 14, further comprising 0.001 to 50% by weight, of a coloring agent, based on the total weight of the electrophotographic toner.

21. (Currently Amended) A composition comprising 30 to 99.99% by weight of a binder, and 0.01 to 50% by weight, of at least one salt of ionic structured silicates ~~in~~ which ~~the cation is~~contains a low molecular weight organic cation and the anion is an island, cyclic, group, chain, ribbon, laminar or matrix silicate or a combination thereof, based on the total weight of the composition, wherein the composition is an electrophotographic toner.

22. (Currently Amended) A method of imparting, controlling or improving the charge of an electrophotographic toner or developer, or an electret material comprising the step of adding a distearyldimethyl ammonium bentonite to a binder of an electrophotographic toner or developer ~~or of a powder coating~~ or of an electret material.